


KNAUF

AMF TOPIQ® Prime



© Frederic Schweizer

AMF TOPIQ® Prime is a very light stone wool panel with a modern, smooth surface.

- Excellent sound absorption ($0.95 \alpha_w$)
- Excellent light reflectance (88%)
- ISO 5
- Ideal for offices, retail, classrooms, learning applications and underground garages

Build on us.

Characteristics		Detailed information							
Edge details		Board	Tegular 24/90		Tegular 15/90				
Additional edge details on request									
Thickness (mm)		15	15		15				
Dimensions (mm)		600 x 600 625 x 625 1200 x 600 1250 x 625	600 x 600 625 x 625 1200 x 600		600 x 600 625 x 625 1200 x 600				
System		Exposed demountable - System C							
Weight		2.4 kg / m²							
Colour		White							
Sound absorption		EN ISO 354		$\alpha_w = 0.95$ as per EN ISO 11654 - Class A					
		Frequency f (Hz)		125	250	500	1000	2000	4000
		α_p		0.50	0.85	0.95	0.90	1.00	1.00
		NRC = 0.90 as per ASTM C 423							
Sound attenuation		EN ISO 10848-2 $D_{n,f,w} = 24 \text{ dB}$ as per EN ISO 717-1 CAC = 24 dB as per ASTM E 413-10							
Sound reduction		EN ISO 10140-2 $R_w = 13 \text{ dB}$ as per EN ISO 717-1							
Fire reaction		Euroclass A1 as per EN 13501-1 Class A as per ASTM E 84							
Light reflectance		88%							
Humidity resistance		100% RH							
Clean room		ISO 5 as per EN ISO 14644-1							
Indoor air quality		 A	 E1	 IAC					
Cleanability									
Sustainability		 28.4% (2023)	 EC 1272/2008 Annex Q	 RTS - EMISSION CLASS 00 BUILDING MATERIAL	 www.blauer-engel.de/uz132				